

(19) World Intellectual Property Organization
International Bureau




(43) International Publication Date
1 February 2001 (01.02.2001)

PCT

(10) International Publication Number
WO 01/07856 A3

- (51) International Patent Classification⁷: F28F 1/00 (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.
- (21) International Application Number: PCT/NL00/00520
- (22) International Filing Date: 21 July 2000 (21.07.2000)
- (25) Filing Language: Dutch
- (26) Publication Language: English
- (30) Priority Data: 1012676 22 July 1999 (22.07.1999) NL
- (71) Applicant (*for all designated States except US*): SPIRO RESEARCH B.V. [NL/NL]; Churchilllaan 52, NL-5705 BK Helmond (NL).
- (72) Inventor; and
- (75) Inventor/Applicant (*for US only*): ROFFELSEN, Franciscus [NL/NL]; Mauritslaan 7, NL-5707 CM Helmond (NL).
- (74) Agent: PRINS, A., W.; Vereenigde, Nieuwe Parklaan 97, NL-2587 BN The Hague (NL).
- (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).
- Published:
— With international search report.
- (88) Date of publication of the international search report:
17 May 2001
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

(54) Title: METHOD FOR MANUFACTURING A DOUBLE-WALLED HEAT EXCHANGING TUBE WITH LEAK DETECTION



(57) Abstract: Method for manufacturing a double-walled heat exchange tube with leak detection, wherein an inner tube is slipped into an outer tube, after a surface profiling has been provided on at least the outer surface of the inner tube or the inner surface of the outer tube, and at least the outer surface of the inner tube or the inner surface of the outer tube has been provided with a layer of soldering material. After the tubes have been slipped into one another, the inner tube is expanded such that the outer tube is expanded as well and the surface profiling forms a leak detection channel between the two tubes, and the soldering material between inner and outer tube is caused to melt. In a heat exchange tube thus obtained, at the location of the contact between the inner and outer tube, a film-thin, optionally porous layer from soldering material is present, which layer is bonded, through melting, to both the inner tube and the outer tube.

200150 52272001

WO 01/07856 A3